

TEST REPORT





Page 1/3

5F Annex Dragon Pearl Plaza 2123 Pudong Avenue Shanghai 200135 - P.R. CHINA Tél.: +86 21 68 55 50 32

Fax: +86 21 68 55 50 33 E-mail: <u>ctcshanghai@ctcgroupe.com</u> Report No.: S171217088_1

29 December 2017

APPLICANT:

 $\textbf{Date of receipt} \hspace{0.3in} : 25 \hspace{0.3in} \text{Dec.} \hspace{0.3in} 2017 \\$

Testing period :25 Dec. 2017

Buyer: -- :29 Dec. 2017

Sample description: 13G cut level 5 HPPE(High Performance Polyethylene) shell coated with grey PU

Style / Article no. : H3101-5 (HW3050)

Test(s) requested :-- For CE Marking : Yes

Service : REGULAR Previous report :--

Brand / Section :-- Product category :-- Season -- Product type :--

End use :-- Test stage :FIRST TEST

Factory name :-- Supplier name :-- Factory code :-- Exported to :--

1. Conclusion:

	Tests description	<u>Conformity</u>	
	EN 388		
1	Puncture resistance: 2016	Level 3	

Pass: requirements met Fail: requirements not met None: no requirement for this test N/A: not applicable

Approved by

Henry YAN Laboratory Supervisor



TEST REPORT





Page 2/3

Report No.: S171217088_1

29 December 2017

APPLICANT:

2. Sample(s) description assigned by laboratory:

<u>Size</u>	Analyzed product	<u>Description</u>	Sample information
	GLOVE		
		Palm	



171217088



TEST REPORT





Page 3/3

Report No.: S171217088_1

29 December 2017

APPLICANT:

3. GLOVE/

Palm

	Method	Client Requirement	Unit	Result	Conformity
(+) 4.1. Puncture resistance:	EN 388 : 2016				
2016					
Puncture resistance			N	104	
Puncture resistance (2)			N	142	
Puncture resistance (3)			N	112	
Puncture resistance (4)			N	122	
Performance level				3	

END OF TEST REPORT

(+)CNAS accreditation

Table of Performance Level for Glove

Test Item	Performance Level					
Tool hom	0##	1	2	3	4	5
Puncture Resistance (EN 388) Force (N) (minimum)	<20	20	60	100	150	

Performance level 0 means the glove falls below the minimum performance level for the given individual hazard