

ANÁLISIS QUÍMICO, PRUEBAS MECÁNICAS Y TÉCNICAS DE INSTALACIÓN

ITEM: NA4060

TEST RESULT

MATERIAL: Q195

ANCHOR SIZE	CODE NO	CHEMICAL										INSTALLATION TECHNICAL			
		C	Si	Mn	P	S	Cr	Ni	Cu	SHEAR STRENG TH	LENGTH ANCHOR	Min	DRILL	Max Fast	PULL OUT
		%	%	%	%	%	%	%	%	t b (mpa)	INCH	Embedment	DIAMETER	Thickness in	LOAD(KGS)
3/4X8-1/2	NA4060	0.07	0.02	0.34	0.01	0.01	0.03	0.01	0.02	338	8-1/2"	108	3/4"	65	4900

Note: THE TEST VALUE LISTED WERE OBTAINED USING 200-250 Kgs/cm² Concrete (no aggregate) a safe working load should not exceed 25% of stated value.

TEST ON WEDGE ANCHORS